

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

AMENDMENTS TO THE CLAIMS:

The following listing of claims replaces all prior listings, and all prior versions, of claims in the application.

LISTING OF CLAIMS:

1. (Currently amended) A cleaning solution for semiconductor substrates, which comprises an oxidizing agent, an acid and a fluorine compound, has a pH adjusted in a range of 3 to 10 by addition of a basic compound and has a concentration of water of 80% by weight or greater, wherein a ratio of an amount by weight of the acid to an amount by weight of the oxidizing agent is in a range of 0.1 to 1,000.
2. (Currently amended) A cleaning solution for semiconductor substrates, which comprises an oxidizing agent, an acid, a fluorine compound and a corrosion inhibitor, has a pH adjusted in a range of 3 to 10 by addition of a basic compound and has a concentration of water of 80% by weight or greater, wherein a ratio of an amount by weight of the acid to an amount by weight of the oxidizing agent is in a range of 0.1 to 1,000.
3. (Cancelled).
4. (Previously presented) A cleaning solution according to Claim 1, wherein the oxidizing agent is hydrogen peroxide.
5. (Previously presented) A cleaning solution according to Claim 1, wherein the oxidizing agent is nitric acid.

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

6. (Previously presented) A cleaning solution according to Claim 1, wherein the acid is an inorganic acid.
7. (Previously presented) A cleaning solution according to Claim 6, wherein the inorganic acid is at least one acid selected from a group consisting of boric acid, sulfamic acid, phosphoric acid and carbonic acid.
8. (Previously presented) A cleaning solution according to Claim 6, wherein the inorganic acid is sulfuric acid.
9. (Previously presented) A cleaning solution according to Claim 1, wherein the acid is an organic acid.
10. (Previously presented) A cleaning solution according to Claim 9, wherein the organic acid is at least one acid selected from a group consisting of oxalic acid, citric acid, propionic acid and acetic acid.
11. (Previously presented) A cleaning solution according to Claim 10, wherein the fluorine compound is ammonium fluoride or tetramethylammonium fluoride.
12. (Previously presented) A cleaning solution according to Claim 1, wherein the basic compound is a strong base having no metal ions.

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

13. (Previously presented) A cleaning solution according to Claim 12, wherein the strong base having no metal ions is tetramethylammonium hydroxide or trimethylhydroxyethylammonium hydroxide.

14. (Previously presented) A cleaning solution according to Claim 2, wherein the corrosion inhibitor is polyethyleneimine.

15. (Previously presented) A cleaning solution according to Claim 1, which further comprises a surfactant.

16. (Original) A cleaning solution according to Claim 15, wherein the surfactant is an anionic surfactant.

17. (Original) A cleaning solution according to Claim 16, wherein the anionic surfactant is a phosphoric ester of a polyoxyethylenealkyl ether or a phosphoric ester of a polyoxyethylenealkyl aryl ether.

18. (Previously presented) A cleaning solution according to Claim 1, adapted for cleaning semiconductor substrates having metal wiring which comprises copper alone or a laminate structure of copper and a barrier metal.

19. (Previously presented) A process for cleaning semiconductor substrates having metal wiring, which comprises cleaning with a cleaning solution described in Claim 1 .

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

20. (Previously presented) A process according to Claim 19, wherein said metal wiring comprises copper alone or a laminate structure of copper and a barrier metal.

21. (Cancelled).

22. (Previously presented) A cleaning solution according to Claim 2, wherein the oxidizing agent is hydrogen peroxide.

23. (Previously presented) A cleaning solution according to Claim 2, wherein the oxidizing agent is nitric acid.

24. (Previously presented) A cleaning solution according to Claim 2, wherein the acid is an inorganic acid.

25. (Previously presented) A cleaning solution according to Claim 24, wherein the inorganic acid is at least one acid selected from a group consisting of boric acid, sulfamic acid, phosphoric acid and carbonic acid.

26. (Previously presented) A cleaning solution according to Claim 24, wherein the inorganic acid is sulfuric acid.

27. (Previously presented) A cleaning solution according to Claim 2, wherein the acid is an organic acid.

Docket No. 396.43501X00

Serial No. 10/777,085

July 7, 2006

28. (Previously presented) A cleaning solution according to Claim 27, wherein the organic acid is at least one acid selected from a group consisting of oxalic acid, citric acid, propionic acid and acetic acid.

29. (Previously presented) A cleaning solution according to Claim 28, wherein the fluorine compound is ammonium fluoride or tetramethylammonium fluoride.

30. (Previously presented) A cleaning solution according to Claim 2, wherein the fluorine compound is ammonium fluoride or tetramethylammonium fluoride.

31. (Previously presented) A cleaning solution according to Claim 1, wherein the fluorine compound is ammonium fluoride or tetramethylammonium fluoride.

32. (Previously presented) A cleaning solution according to Claim 2, wherein the basic compound is a strong base having no metal ions.

33. (Previously presented) A cleaning solution according to Claim 32, wherein the strong base having no metal ions is tetramethylammonium hydroxide or trimethylhydroxyethylammonium hydroxide.

34. (Previously presented) A cleaning solution according to Claim 2, which further comprises a surfactant.

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

35. (Previously presented) A cleaning solution according to Claim 34, wherein the surfactant is an anionic surfactant.

36. (Previously presented) A cleaning solution according to Claim 35, wherein the anionic surfactant is a phosphoric ester of a polyoxyethylenealkyl ether or a phosphoric ester of a polyoxyethylenealkyl aryl ether.

37. (Previously presented) A cleaning solution according to Claim 2, adapted for cleaning semiconductor substrates having metal wiring which comprises copper alone or a laminate structure of copper and a barrier metal.

38. (Previously presented) A cleaning solution according to Claim 15, adapted for cleaning semiconductor substrates having metal wiring which comprises copper alone or a laminate structure of copper and a barrier metal.

39. (Previously presented) A process for cleaning semiconductor substrates having metal wiring, which comprises cleaning with a cleaning solution described in Claim 2.

40. (Previously presented) A process for cleaning semiconductor substrates having metal wiring, which comprises cleaning with a cleaning solution described in Claim 15.

Docket No. 396.43501X00
Serial No. 10/777,085
July 7, 2006

41. (New) A cleaning solution according to Claim 1, wherein said ratio of an amount by weight of the acid to the amount by weight of the oxidizing agent is in a range of 1.0 to 100.

42. (New) A cleaning solution according to Claim 41, wherein said ratio is in a range of 1 to 60.

43. (New) A cleaning solution according to Claim 1, wherein amount of said fluorine compound in the solution is 0.001 to 15% by weight.

44. (New) A cleaning solution according to Claim 2, wherein said ratio of an amount by weight of the acid to the amount by weight of the oxidizing agent is in a range of 1.0 to 100.

45. (New) A cleaning solution according to Claim 44, wherein said ratio is in a range of 1 to 60.

46. (New) A cleaning solution according to Claim 2, wherein amount of said fluorine compound in the solution is 0.001 to 15% by weight.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.